

Technical data sheet

ALBERDINGK® AC 2019

Characteristic:

Aqueous, fine disperse, APEO-free copolymer dispersion without plasticizers and protective colloids.

Specification:

Solids content	%	45.0 - 47.0
----------------	---	-------------

According to:

ISO 3251
1.0 g weighed quantity at
105°C

pH- value		8.0 - 9.0
-----------	--	-----------

ISO 976

Viscosity	mPas	500 - 1500
-----------	------	------------

ISO 2555, Brookfield RVT
Spindle 2/rpm 20/factor 20

Further typical data*:

MFFT	°C	ca. 17
------	----	--------

According to:

Density	g/cm ³	1.0 - 1.1
---------	-------------------	-----------

ISO 2811-1

Highlights:

- very low water absorption
- very good weathering resistance

Applications:

Recommended for facade paints, plasters, enamels, coatings for fibre cement and wood stains.

Technical data sheet

ALBERDINGK® AC 2019

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Packaging:

plastic drums (120 kg)
one-way container (approx. 1000 kg)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the current safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.