

# Technical data sheet

## ALBERDINGK® AC 2511

### Characteristic:

ALBERDINGK® AC 2511 is an aqueous, fine disperse polymer dispersion (surfactant type) without plasticizers and protective colloids.

### Specification:

Solids content	%	41.0 - 43.0
----------------	---	-------------

### According to:

ISO 3251  
1.0 g weighed quantity at 105°C

pH- value		7.5 - 9.0
-----------	--	-----------

ISO 976

Viscosity	mPas	20 - 150
-----------	------	----------

ISO 2555, Brookfield RVT  
Spindle 1/rpm 50/factor 2

### Further typical data\*:

MFFT	°C	ca. 100
------	----	---------

### According to:

Density	g/cm <sup>3</sup>	1.0 - 1.1
---------	-------------------	-----------

ISO 2811-1

Glass transition temperature	°C	ca. 100
------------------------------	----	---------

DSC, heating rate 20 K/min

### Applications:

Leather treatment and leather coating. Useful as an additive in aqueous coatings for an increase of the blocking temperature.

# Technical data sheet

## ALBERDINGK® AC 2511

### Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

### Packaging:

plastic drums (120 kg)  
one-way container (approx. 1000 kg)  
as bulk in tank cars, by agreement.

### Safety:

For further information on product safety please refer to the current safety data sheet.

### Notice:

\* General information - the values can not be considered as part of the product specification.