

Technical data sheet

ALBERDINGK® AC 2529 A

Characteristic:

Aqueous, fine disperse copolymer dispersion without plasticizers and protective colloids.

Specification: Solids content	%	43.0 - 45.0	According to: ISO 3251 1.0 g weighed quantity at 105°C
pH- value Viscosity	mPas	6.5 - 8.0 100 - 1000	ISO 976 ISO 2555, Brookfield RVT Spindle 2/rpm 20/factor 20
Further typical data*:			According to:
MFFT	°C	ca. 50	
Density	g/cm3	1.0 - 1.1	ISO 2811-1
Solvent-free			
Film properties*:			According to:

Applications:

Pendulum hardness (König) s

Wood coating systems with high gloss. Good compatibility with ALBERDINGK polyurethane dispersions e. g. ALBERDINGK® U 3251, ALBERDINGK® U 8002, and ALBERDINGK® U 9800.

ca. 130

ISO 1522

Latest update 01.03.2024

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 1 of 2

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com



Technical data sheet

ALBERDINGK® AC 2529 A

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Packaging:

plastic drums (120 kg) one-way container (approx. 1000 kg) as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the current safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.

Latest update 01.03.2024

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 2 of 2

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com