

# Technical data sheet

## ALBERDINGK® AC 75032

### Characteristic:

Aqueous, low viscous dispersion of acrylic acid ester copolymer without plasticizer, protective colloid (APEO-free).

### Specification:

Solids content	%	59.0 - 61.0
----------------	---	-------------

### According to:

ISO 3251  
1.0 g weighed quantity at 105°C

pH- value		5.0 - 6.0
-----------	--	-----------

ISO 976

Viscosity	mPas	500 - 1500
-----------	------	------------

ISO 2555, Brookfield RVT  
Spindle 2/rpm 20/factor 20

### Further typical data\*:

MFFT	°C	ca. 0
------	----	-------

### According to:

Density	g/cm <sup>3</sup>	1.0 - 1.1
---------	-------------------	-----------

ISO 2811-1

Glass transition temperature	°C	ca. -40
------------------------------	----	---------

DSC, heating rate 20 K/min

### Properties:

The films are permanent tacky with a very high tack, very high water resistance and a reduced blushing. The films retain their mechanical strength and adhesion under cold water storage.

### Applications:

Suitable for self sticky articles e.g. labels, tapes and foils. Good adhesion especially on aluminium.

# Technical data sheet

## ALBERDINGK® AC 75032

### Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

### Packaging:

plastic drums (120 kg)  
one-way container (approx. 1000 kg)  
as bulk in tank cars, by agreement.

### Safety:

For further information on product safety please refer to the current safety data sheet.

### Notice:

\* General information - the values can not be considered as part of the product specification.