

Preliminary technical data sheet

ALBERDINGK® AFU 4200 VP

Characteristic:

"AFU" = Amine Free Urethane.

Solvent- and amine-free, aliphatic polyurethane dispersion.

Specification:

Solids content	%	32.0 - 34.0
----------------	---	-------------

According to:

ISO 3251
0.5 g weighed quantity at
105°C

pH- value		7.5 - 8.5
-----------	--	-----------

ISO 976

Viscosity	mPas	50 - 500
-----------	------	----------

ISO 2555, Brookfield RVT
Spindle 1/rpm 50/factor 2

Further typical data*:

MFFT	°C	ca. 0
------	----	-------

According to:

Density	g/cm ³	1.0 - 1.1
---------	-------------------	-----------

ISO 2811-1

Solvent-free

Applications:

Highly suited as primer on plastic substrates (e.g. corona treated BOPP). The polymer film can be easily recoated with other materials.

Preliminary technical data sheet

ALBERDINGK® AFU 4200 VP

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Packaging:

plastic drums (120 kg)
one-way container (approx. 1000 kg)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the current safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.