

Technical data sheet

ALBODUR® 912

Characteristic:

OH-functional polyol based on castor oil (renewable raw materials).

Specification:

Acid value	mg KOH/g	1.0 - 2.0	According to: ISO 660
Water content	%	0.00 - 0.30	ISO 8534
Iodine colour value		2.0 - 4.0	DIN 6271
Gardner colour value		2.0 - 4.0	ISO 4630
Hydroxyl value	mg KOH/g	200 - 230	ISO 4629-2
Viscosity acc. to Brookfield cone plate at 25°C, cone 5, 500rpm	mPas	500 - 800	ISO 2884

Further typical data*:

Non-volatile compounds	%	ca. 100	According to:
OH-content as supplied	%	ca. 6.29	
OH-equivalent weight		ca. 270	
Solvent-free			
Density at 23°C	g/cm ³	0.97 - 0.98	ISO 2811-3
Shore A hardness		ca. 95	ISO 48-4
Shore D hardness		ca. 45	ISO 48-4
Elongation at break	%	ca. 165	ISO 527-1
Tensile strength	N/mm ²	ca. 15	ISO 527-1

Applications:

If crosslinked with e.g. an aromatic polyisocyanate, medium hard surface coatings with good chemical resistance are obtained.

Technical data sheet

ALBODUR® 912

Storage:

In originally closed containers, ALBODUR® 912/ 921 is stable for 6 months when stored at recommended temperature range from +10°C to +30°C.

The products should be protected from atmospheric oxygen.

A turbidity of the products due to low temperature transport or storage can be reduced by heating up to more than 40 °C. The optical change does not have any negative impact on the product properties.

ALBERDINGK BOLEY GmbH assures, that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH.

Packaging:

steel drums (190 kg)

one-way container (approx. 900 kg)

as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the current safety data sheet.

Notice:

* General information - the values cannot be considered as part of the product specification.

The measurements of the shore hardness as well as elongation at

break and tensile strength are performed by the following formulation:

94.5% ALBODUR® + 5.0% ALBOLITH MS C 350 + 0.5% BYK-088 (BYK Chemie). Crosslinked with Suprasec 2496 (Huntsman). Crosslinking ratio 110%.

The results are measured after curing 7 days at RT.