

Technical data sheet

ALBODUR® 924

Characteristic:

OH-functional polyol based on castor oil (renewable raw materials).

Specification:

			According to:
Acid value	mg KOH/g	0.00 - 2.00	ISO 660
Water content	%	0.00 - 0.10	ISO 8534
Gardner colour value		2.0 - 5.0	ISO 4630
Iodine colour value		2.0 - 5.0	DIN 6271
Viscosity acc. to Brookfield cone plate at 25°C, cone 5, 500upm	mPas	1000 - 3000	ISO 2884
Hydroxyl value	mg KOH/g	220 - 250	ISO 4629-2

Further typical data*:

			According to:
Non-volatile compounds	%	ca. 100	
OH-content as supplied	%	ca. 7.0	
OH-equivalent weight		ca. 242	
Shore A hardness		ca. 98	ISO 48-4
Shore D hardness		ca. 65	ISO 48-4
Elongation at break	%	ca. 40	ISO 527-1
Tensile strength	N/mm ²	ca. 20	ISO 527-1
Solvent-free			

Applications:

If crosslinked with e.g. an aromatic polyisocyanate, hard surface coatings with good chemical resistance are obtained. The product is especially suitable for electro castings.

Technical data sheet

ALBODUR® 924

Storage:

In originally closed containers, ALBODUR® polyols and oil polymers are stable for 6 months when stored at recommended temperature range from +5°C to +30°C. The products should be protected from atmospheric oxygen.

A turbidity of the products due to coldness is reversible and can be removed by heating up to more than 40 °C.

ALBERDINGK BOLEY GmbH assures, that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH.

Packaging:

steel drums (190 kg)
one-way container (approx. 900 kg)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the current safety data sheet.

Notice:

* General information - the values cannot be considered as part of the product specification.

The measurements of the shore hardness as well as elongation at break and tensile strength are performed by the following formulation: 94.5% ALBODUR® + 5.0% ALBOLITH MS C 350 + 0.5% BYK-088 (BYK Chemie). Crosslinked with Suprasec 2496 (Huntsman). Crosslinking ratio 110%.

The results are measured after curing 7 days at RT.