

Preliminary technical data sheet

ALBERDINGK® AS 2120 VP

Characteristic:

Anionic, silane modified styrene acrylic dispersion.

Specification: Solids content	%	49.0 - 51.0	According to: ISO 3251 1.0 g weighed quantity at 105°C
pH- value Viscosity	mPas	7.0 - 8.0 500 - 2000	ISO 976 ISO 2555, Brookfield RVT Spindle 2/rpm 20/factor 20
Further typical data*:			According to:
MFFT	°C	ca. 17	
Density	g/cm3	1.0 - 1.1	ISO 2811-1
Solvent-free			
Glass transition temperature	°C	ca. 20	DSC, heating rate 20 K/min

Applications:

Suitable for waterproofing, cement-free tile adhesives as well as primer on difficult substrates (e.g. tiles).

Packaging:

plastic drums (120 kg) one-way container (approx. 1000 kg) as bulk in tank cars, by agreement.

Latest update 29.07.2023

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 1 of 2

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com



Preliminary technical data sheet

ALBERDINGK® AS 2120 VP

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Safety:

For further information on product safety please refer to the current safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.

Latest update 29.07.2023

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 2 of 2

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com