

# Technical data sheet

## ALBERDINGK® AS 2685

### Characteristic:

ALBERDINGK® AS 2685 is an aqueous, fine disperse copolymer dispersion of an acrylic acid ester and styrol.

### Specification:

Solids content	%	42.0 - 44.0
pH- value		7.0 - 8.0
Viscosity	mPas	2000 - 4500

### According to:

ISO 3251  
1.0 g weighed quantity at 105°C  
ISO 976  
ISO 2555, Brookfield RVT  
Spindle 3/rpm 20/factor 50

### Further typical data\*:

MFFT	°C	ca. 20
Density	g/cm <sup>3</sup>	1.0 - 1.1

### According to:

ISO 2811-1

### Film properties\*:

Pendulum hardness (König)	s	ca. 45
---------------------------	---	--------

### According to:

ISO 1522

### Applications:

For wood, metal and plastic coatings. Alone or in combination with polyurethane dispersions.

# Technical data sheet

## ALBERDINGK® AS 2685

### Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

### Packaging:

plastic drums (120 kg)  
one-way container (approx. 1000 kg)  
as bulk in tank cars, by agreement.

### Safety:

For further information on product safety please refer to the current safety data sheet.

### Notice:

\* General information - the values can not be considered as part of the product specification.