

Technical data sheet

ALBERDINGK® Castor Oil PD

Characteristic:

Castor oil PD is a partially dehydrated castor oil produced in a special process (conversion of the ricinolic acid in 9.11 - conjugated - and 9.12 - isolated - linoleic acid).

Specification:

			According to:
Acid value	mg KOH/g	3.0 - 5.0	ISO 660
Water content	%	0.00 - 0.10	ISO 8534
Iodine colour value		2.0 - 4.0	DIN 6271
Gardner colour value		2.0 - 4.0	ISO 4630
Viscosity acc. to Brookfield cone plate at 25°C, cone 5, 500upm	dPas	4.0 - 8.0	ISO 2884
Hydroxyl value	mg KOH/g	110 - 130	ISO 4629-2

Further typical data*:

			According to:
Density at 23°C	g/cm ³	0.94 - 0.96	ISO 2811-3

Applications:

Castor oil PD is a diol with plasticizing and hydrophobing properties for polyurethane systems, e.g. varnishes, casting resins, foams and moulded components.

Storage:

The storage life can be guaranteed for minimum 12 months in tightly locked containers and at a temperature of + 10 °C up to + 30 °C.

A turbidity of the oil due to coldness is reversible and can be removed by heating up to more than 40 °C.

Safety:

For further information on product safety please refer to the current safety data sheet.

Technical data sheet

ALBERDINGK® Castor Oil PD

Notice:

* General information - the values can not be considered as part of the product specification.

Latest update
16.04.2024

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 2 of 2

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com
Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required.

