

Preliminary technical data sheet

ALBERDINGK® CUD 4820 VP

Characteristic:

Solvent-free, aliphatic, cationic Polycarbonat Polyurethane dispersion.

Specification: Solids content	%	34.0 - 36.0	According to: ISO 3251 0.5 g weighed quantity at 105°C
pH- value Viscosity	mPas	4.0 - 6.0 20 - 200	ISO 976 ISO 2555, Brookfield RVT Spindle 1/rpm 20/factor 5
Further typical data*: MFFT Density Solvent-free	°C g/cm3	ca. 21 1.0 - 1.1	According to: ISO 2811-1

Applications:

Suitable for metal coatings - softer version of CUD 4835 VP.

 Latest update
 Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany

 23.06.2016
 Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

 Page 1 of 2
 Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com

 Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com

 The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from thisinformation. Industrial property rights are to be considered if required.



Preliminary technical data sheet

ALBERDINGK® CUD 4820 VP

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Packaging:

plastic drums (120 kg) one-way container (approx. 1000 kg) as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the current safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.

Latest update	Alberdingk Boley GmbH Düsseldorfer Str. 53 47829 Krefeld Germany		
23.06.2016	Phone +49 2151 528-0 Fax +49 2151 573643 info@alberdingk-boley.de www.alberdingk-boley.de		
Page 2 of 2	Alberdingk Boley, Inc. Greensboro, NC, USA www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. Shenzhen City, P.R. China www.alberdingkchina.com		
	The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from thisinformation. Industrial property rights are to be considered if required.		