

## Technical data sheet

## ALBERDINGK® Linseed Oil Fatty Acid

Specification: Acid value			According to: ISO 660
Acid value	mg KOH/g	100 - 150	ISO 660
Water content			ISO 8534
Water content	%	max. 2.5	ISO 8534
Further typical data*:			According to:
Gardner colour value		min. 18	ISO 4630
Saponification value	mg KOH/g	160 - 200	ISO 12966
Iodine value acc. to Wijs	g Iod/100g	j 140 - 200	ISO 12966
Density at 20°C	g/cm3	ca. 0.93	ISO 2811-3
Unsaponifiable content	%	max. 5	Ph. Eur. 2.5.7
Linolenic acid content	%	ca. 30 - 50	ISO 12966

## Safety:

For further information on product safety please refer to the current safety data sheet.

## Notice:

\* General information - the values can not be considered as part of the product specification.

Latest update 20.04.2021

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 1 of 1

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from thisinformation. Industrial property rights are to be considered if required.