

## Technical data sheet

## ALBERDINGK® Pale Refined Linseed Oil

### **Characteristic:**

Pale refined linseed oil is a slime free refined oil produced from raw linseed oil, won by a refining process going over the steps of degumming, neutralising and bleaching. The extra pale colour value is achieved by a special bleaching process.

Specification:			According to:
Acid value	mg KOH/g	max. 1	ISO 660
Gardner colour value		max. 2.5	ISO 4630
Iodine value acc. to Wijs	g Iod/100g	, min. 175	ISO 12966
Further typical data*:			According to:
Refractive index		1.4785 -	ISO 6320
		1.4825	
Saponification value	mg KOH/g	188 - 195	ISO 12966
Viscosity acc. to Höppler	dPas	0.45 - 0.50	ISO 12058-1
at 20°C			
Density at 20°C	g/cm3	0.926 - 0.933	ISO 2811-3
Water content	%	max. 0.1	ISO 8534

### **Applications:**

Pale refined linseed oil is used for the production of oil modified polyester resins (i.e. alkyd resins), stand oils, printing varnishes, maleate and urethane oils in the synthetic resins, coatings and printing ink industry. It also finds application as a binder in pigment pastes.

Latest update 20.04.2021

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 1 of 2

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from thisinformation. Industrial property rights are to be considered if required.



# Technical data sheet

### ALBERDINGK® Pale Refined Linseed Oil

### **Properties:**

As a triglyceride, Pale refined linseed oil belongs to the fast drying vegetable oils with a high portion of unsaturated fatty acids - about 50 - 60% linolenic acid, 14 - 18% linoleic acid and 17 - 24% oleic acid. In contact with air, accelerated by driers (siccatives), linseed oil forms hard films with excellent stability and good colour- and gloss-retention.

### Storage:

The storage life can be guaranteed for minimum 12 months in tightly locked containers and at a temperature of + 10 °C up to + 30 °C. A turbidity of the oil due to coldness is reversible and can be removed by heating up to more than 40 °C.

### Safety:

For further information on product safety please refer to the current safety data sheet.

### **Notice:**

\* General information - the values can not be considered as part of the product specification.

Latest update 20.04.2021

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 2 of 2

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from thisinformation. Industrial property rights are to be considered if required.