

Technical data sheet

ALBERDINGK® LUX 220

Characteristic:

Water based, solvent free, UV curing polyurethane dispersion

Specification:			According to:
Solids content	%	34.0 - 36.0	ISO 3251
			0.5 g weighed quantity at
			105°C
pH- value		7.0 - 9.0	ISO 976
Viscosity	mPas	20 - 200	ISO 2555, Brookfield RVT
			Spindle 1/rpm 50/factor 2
Further typical data*:			According to:
MFFT	°C	ca. 0	
Density	g/cm3	1.0 - 1.1	ISO 2811-1
Solvent-free			
Pilos anno anticova			A consulting to
Film properties*:			According to:
Pendulum hardness (König)	S	ca. 180	ISO 1522
after UV-curing			
Pendulum hardness (König)	S	ca. 50	ISO 1522
before UV-curing			

Applications:

Highly suitable for coatings on wood and PVC with very high chemical resistance. Thanks to it's high film hardness, the dispersion can be used especially for pigmented coatings and on-site UV cure varnishes. Furthermore, it offers a very high crosslinking density which yields in films offering very high abrasion resistance, stain resistance and solvent resistance.

Latest update 23.11.2017

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 1 of 3

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com



Technical data sheet

ALBERDINGK® LUX 220

Curing recommendations:

Photoinitiator (e.g. Omnirad 500 (former Irgacure 500)): 1% on the delivered form.

Belt speed: 5 - 10 m/min., 1 Hg-lamp 80 W/cm

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Packaging:

plastic drums (120 kg) one-way container (approx. 1000 kg) as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the current safety data sheet.

Latest update 23.11.2017

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 2 of 3

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from thisinformation. Industrial property rights are to be considered if required.



Technical data sheet

ALBERDINGK® LUX 220

Notice:

* General information - the values can not be considered as part of the product specification.

Latest update 23.11.2017

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 3 of 3

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from thisinformation. Industrial property rights are to be considered if required.