ALBERDINGK BOLEY

Technical data sheet

ALBERDINGK® OP 100

Characteristic:

A 100% solids urethane modified oil polymer based on linseed oil.

Specification:			**According to:**
Solids content	%	ca. 100	ISO 3251
Acid value	mg KOH/g	ca. 0.3	ISO 660
Gardner colour value		ca. 5	ISO 4630
Viscosity acc. to Brookfield cone plate at 20°C, cone 1, 100upm	mPas	ca. 800	Reference ISO 12058-1

Further typical data*:

Solvent-free

Applications:

For woodcare products based on renewable resources. Polymer according to REACH legislation that is diluted in linseed oil. It is recommended to add siccatives for fast and proper drying.

Storage:

In originally closed containers, ALBODUR® polyols and oil polymers are stable for 12 months when stored at recommended temperature range from +5°C to +30°C. The products should be protected from atmospheric oxygen.
A turbidity of the products due to coldness is reversible and can be removed by heating up to more than 40 °C.
ALBERDINGK BOLEY GmbH assures, that the data mentioned under "specification" are stable for 12 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 12 months of storage can not be given by ALBERDINGK BOLEY GmbH.

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com
Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from thisinformation. Industrial property rights are to be considered if required.

ALBERDINGK BOLEY

Technical data sheet

ALBERDINGK® OP 100

Packaging:
steel drums (190 kg)
one-way container (approx. 900 kg)
as bulk in tank cars, by agreement.

Safety:
For further information on product safety please refer to the current safety data sheet.

Notice:
* General information - the values can not be considered as part of the product specification.

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com
Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from thisinformation. Industrial property rights are to be considered if required.