

# Preliminary technical data sheet

## ALBERDINGK® Ren U 228 VP

### **Characteristic:**

Soft, solvent free, aliphatic polyether-polyurethane dispersion based on renewable resources.

<b>Specification:</b> Solids content	%	56.0 - 58.0	According to: ISO 3251 0.5 g weighed quantity at 105°C
pH- value Viscosity	mPas	7.5 - 9.5 200 - 1000	ISO 976 ISO 2555, Brookfield RVT Spindle 2/rpm 20/factor 20
Further typical data*:			According to:
MFFT	°C	ca. 0	
Density Solvent-free	g/cm3	1.0 - 1.1	ISO 2811-1

### **Applications:**

For flat-roof coatings, or also for soft and flexible coating systems on e.g. leather, textile and plastics.

#### **Highlights:**

The biobased content is approx. 64% (on solids).

 Latest update
 Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany

 25.08.2020
 Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

 Page 1 of 2
 Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com

 Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com

 The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from thisinformation. Industrial property rights are to be considered if required.



# Preliminary technical data sheet

### ALBERDINGK® Ren U 228 VP

### Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

### **Packaging:**

plastic drums (120 kg) one-way container (approx. 1000 kg) as bulk in tank cars, by agreement.

#### Safety:

For further information on product safety please refer to the current safety data sheet.

### **Further information:**

The product tends to form sedimentation, so it has to be stirred very well before use.

### **Notice:**

\* General information - the values can not be considered as part of the product specification.

Latest update	Alberdingk Boley GmbH   Düsseldorfer Str. 53   47829 Krefeld   Germany
25.08.2020	Phone +49 2151 528-0   Fax +49 2151 573643   info@alberdingk-boley.de   www.alberdingk-boley.de
Page 2 of 2	Alberdingk Boley, Inc.   Greensboro, NC, USA   www.alberdingkusa.com
	Alberdingk Resins (Shenzhen) Co.Ltd.   Shenzhen City, P.R. China   www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required.