

Technical data sheet

ALBERDINGK® U 2101

Characteristic:

Aqueous, solvent-free, anionic dispersion of an aliphatic polyester-polyurethane without solvents and free isocyanate groups. High elasticity with a soft feeling.

Specification: Solids content	%	59.5 - 61.5	According to: ISO 3251 0.5 g weighed quantity at 105°C
pH- value Viscosity	mPas	7.5 - 9.5 600 - 1400	ISO 976 ISO 2555, Brookfield RVT Spindle 2/rpm 20/factor 20
Further typical data*:			According to:
MFFT	°C	ca. 0	
Density	g/cm3	1.0 - 1.1	ISO 2811-1
Solvent-free			
Film properties*:			According to:
Blocking point	°C	ca. 110	
Pendulum hardness (König)	S	ca. 30	ISO 1522
E-Modulus	N/mm2	ca. 1.5	ISO 527-1
Ultimate tensile strength	N/mm2	ca. 19	ISO 527-1
Elongation at break	%	ca. 800	ISO 527-1

Applications:

Coating systems for the leather, textile and plastic industry.

Latest update 10.06.2016

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 1 of 2

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from thisinformation. Industrial property rights are to be considered if required.



Technical data sheet

ALBERDINGK® U 2101

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Packaging:

plastic drums (120 kg) one-way container (approx. 1000 kg) as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the current safety data sheet.

Further information:

The product tends to form sedimentation, so it has to be stirred very well before use.

Notice:

* General information - the values can not be considered as part of the product specification.

Latest update	Alberdingk Boley GmbH Düsseldorfer Str. 53 47829 Krefeld Germany
10.06.2016	Phone +49 2151 528-0 Fax +49 2151 573643 info@alberdingk-boley.de www.alberdingk-boley.de
Page 2 of 2	Alberdingk Boley, Inc. Greensboro, NC, USA www.alberdingkusa.com
	Alberdingk Resins (Shenzhen) Co.Ltd. Shenzhen City, P.R. China www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required.