

# Preliminary technical data sheet

# ALBERDINGK® U 6154 VP

### Characteristic:

Aqueous, low viscous, anionic, solvent-free dispersion of an aliphatic polycarbonate-polyurethane without free isocyanate groups.

### Specification:

Solids content	%	37.0 - 39.0
----------------	---	-------------

**According to:**

ISO 3251  
0.5 g weighed quantity at  
105°C

pH- value 7.5 - 9.0

Viscosity	mPas	20 - 200
-----------	------	----------

ISO 976

ISO 2555, Brookfield RVT  
Spindle 1/rpm 20/factor 5

### Further typical data\*:

MFFT °C ca. 13

Density	g/cm <sup>3</sup>	1.0 - 1.1
---------	-------------------	-----------

**According to:**

ISO 2811-1

Solvent-free

## Applications:

This polycarbonate containing polyurethane dispersion has a very good levelling and chemical resistance. Very good combination possibilities with polyester-polyurethane and acrylic dispersions.

# Preliminary technical data sheet

## ALBERDINGK® U 6154 VP

### Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

### Packaging:

plastic drums (120 kg)  
one-way container (approx. 1000 kg)  
as bulk in tank cars, by agreement.

### Safety:

For further information on product safety please refer to the current safety data sheet.

### Notice:

\* General information - the values can not be considered as part of the product specification.