

# Technical data sheet

## ALBERDINGK® U 9000

### Characteristic:

Waterbased, aliphatic polycarbonate polyurethane dispersion with N-Butylpyrrolidone.

### Specification:

Solids content	%	27.0 - 30.0
----------------	---	-------------

### According to:

ISO 3251  
0.5 g weighed quantity at 150°C

pH- value		7.0 - 8.5
-----------	--	-----------

Viscosity	mPas	50 - 1000
-----------	------	-----------

ISO 976

ISO 2555, Brookfield RVT  
Spindle 2/rpm 20/factor 20

### Further typical data\*:

MFFT	°C	ca. 0
Density	g/cm <sup>3</sup>	1.0 - 1.1
Organic solvent (N-Butylpyrrolidone)	%	ca. 10.9

### According to:

ISO 2811-1

### Applications:

For metal pre-treatment with very good corrosion resistance and excellent chemical resistance.

# Technical data sheet

## ALBERDINGK® U 9000

### Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

### Packaging:

plastic drums (120 kg)  
one-way container (approx. 1000 kg)  
as bulk in tank cars, by agreement.

### Safety:

For further information on product safety please refer to the current safety data sheet.

### Notice:

\* General information - the values can not be considered as part of the product specification.