

# Technical data sheet

# ALBERDINGK® U 9380

### **Characteristic:**

Aqueous, colloidal, anionic, low viscous dispersion of an aliphatic polyester-polyurethane without free isocyanate groups.

<b>Specification:</b> Solids content	%	31.0 - 34.0	According to: ISO 3251 0.5 g weighed quantity at 105°C
pH- value Viscosity	mPas	7.5 - 9.0 10 - 250	ISO 976 ISO 2555, Brookfield RVT Spindle 1/rpm 20/factor 5
Further typical data*: MFFT Density Solvent-free	°C g/cm3	ca. 25 1.0 - 1.1	According to: ISO 2811-1

## **Applications:**

Coating systems with good chemical resistance.

Applications: plastic and wood coatings as well as good compatibility with acrylic dispersions.

Latest update 03.08.2016

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 1 of 2

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com



# Technical data sheet

## ALBERDINGK® U 9380

#### Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

## Packaging:

plastic drums (120 kg) one-way container (approx. 1000 kg) as bulk in tank cars, by agreement.

#### Safety:

For further information on product safety please refer to the current safety data sheet.

### **Notice:**

\* General information - the values can not be considered as part of the product specification.

Latest update 03.08.2016

Alberdingk Boley GmbH | Düsseldorfer Str. 53 | 47829 Krefeld | Germany Phone +49 2151 528-0 | Fax +49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 2 of 2

Alberdingk Boley, Inc. | Greensboro, NC, USA | www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com