

Technical data sheet

ALBERDINGK® VA 294

Characteristic:

Aqueous, medium viscous copolymer dispersion of vinyl acetate and acrylic acid esters with protective colloid and free of plasticizers. APEO-free version of ALBERDINGK VA 292.

Specification:

Solids content	%	51.0 - 53.0	According to: ISO 3251 1.0 g weighed quantity at 105°C
pH- value		4.0 - 5.0	ISO 976
Viscosity	mPas	2500 - 6000	ISO 2555, Brookfield RVT Spindle 2/rpm 5/factor 80

Further typical data*:

MFFT	°C	ca. 7	According to:
Density	g/cm ³	1.0 - 1.1	ISO 2811-1
Average particle size		ca. 0.2	

Film properties*:

Water absorption	%	ca. 25	According to:
Ultimate tensile strength	N/mm ²	ca. 6	ISO 527-1
Elongation at break	%	ca. 1400	ISO 527-1
Glass transition temperature	°C	ca. 15	DSC, heating rate 20 K/min

Properties:

Films formed of the dispersion are clear, very flexible and have a good water and alkali resistance.

Applications:

Universally applicable for indoor and outdoor coatings from matt to gloss. Especially suitable as a binder for full colours and tinting pastes.

Technical data sheet

ALBERDINGK® VA 294

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Packaging:

plastic drums (120 kg)
one-way container (approx. 1000 kg)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the current safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.