

Linseed oils

Name	Properties
ALBERDINGK® Crude Linseed Oil	Water content max.: 0.20 % Saponification value max: 195 mg KOH/g Iodine value acc. to Wijs: 175.0000 - 210.0000 g Iod/100g Gardner color: 0.0 - 13.0 Acid Value: 0.0 - 2.7 mg KOH/g
ALBERDINGK® Double Boiled Linseed Oil	Water content max.: 0.20 % Viscosity (Hoeppler): 0.70 - 1.00 dPas Saponification value max: 200 mg KOH/g Gardner color: 8.0 - 12.0 Applications: Wood > Wood Care Applications: Natural paints Applications: Oil paints Acid Value: 0.0 - 5.0 mg KOH/g
ALBERDINGK® Refined Linseed Oil	Water content max.: 0.10 % Viscosity (Hoeppler): 0.45 - 0.50 dPas Saponification value max: 195 mg KOH/g Iodine value acc. to Wijs: 175.0000 - 210.0000 g Iod/100g Gardner color: 0.0 - 4.0 Applications: Natural paints Applications: Wood > Wood Care Applications: Oil paints Applications: Pigment pastes Applications: Printing inks Applications: Alkyd resins Acid Value: 0.0 - 1.0 mg KOH/g
ALBERDINGK® Refined Linseed Oil Winterized	Water content max.: 0.10 % Viscosity (Hoeppler): 0.45 - 0.50 dPas Saponification value max: 195 mg KOH/g Iodine value acc. to Wijs: 175.0000 - 210.0000 g Iod/100g Gardner color: 0.0 - 4.0 Applications: Natural paints Applications: Oil paints Acid Value: 0.0 - 1.0 mg KOH/g