

## Hydrosols

Name	Properties
ALBERDINGK® H 595	pH-value : 7.5 - 9.0 Viscosity (Brookfield RVT): 20 - 35 mPas Solids content: 29.0 - 31.0 Self crosslinking (SXL): No Multi phase: No Minimum film forming temperature (MFFT): 0 °C Applications: Building & Construction Applications: Building & Construction > Impregnation
ALBERDINGK® H 735	pH-value : 7.0 - 9.0 Viscosity (Brookfield RVT): 20 - 200 mPas Solids content: 34.0 - 36.0 Self crosslinking (SXL): No Multi phase: No Minimum film forming temperature (MFFT): 0 °C Applications: Building & Construction > Impregnation Applications: Flooring Applications: Flooring > Concrete Applications: Building & Construction