









Dispersions for decorative applications

Content

ALBERDINGK BOLEY in a nutshell	4
Introduction	7
Interior paint binders	7
Styrene acrylics & pure acrylics	7
Styrene acrylic for silicate and preservative free paints	8
Multiphase acrylics for high stain resistant paints	8
Renewable resource PUD & Acrylics.....	9
Primers / stabilisers	10
Hydrosol	10
Exterior paints.....	11
Pure acrylics	11
Styrene acrylics	12
Binders for renders / plasters.....	13
Binders for colour quartz renders.....	14
Fast drying acrylics for autumn / spring.....	15
PUDs for exterior coatings	16
Binders for multicolour paints (MCP)	18
Enamels / lacquers / trim paints / stains	19
Acrylics for enamels.....	19
Improved open time acrylics	20
Acrylics for stick to anything paints	24
Acrylics for trim paints	25
Binders for stains	26
Metal paints.....	27
Stain locking primers	29
Floor paints	30
Varnishes	31
Construction products	32
Waterproofing.....	32
Grouts and mortars	34
Ceramic tiles	34

ALBERDINGK BOLEY in a nutshell

 <p>Leading global manufacturer of environmentally friendly water-based binders and oils with unique properties to refine, refurbish, bind and protect multiple types of substrates</p>	 <p>Medium sized, privately owned company</p> <p>> a partner to our customers for more than 250 years</p>	 <p>> 500 employees</p>
 <p>Dynamic, Innovative and flexible</p> <p>Pioneers in biobased polymer dispersions</p>	 <p>Dispersions: Acrylic, Vinyl acetate, Polyurethane and hybrid dispersions</p> <p>Oils: Linseed oil, Castor oil, Derivatives</p>	 <p>Locations:</p> <ul style="list-style-type: none"> • Krefeld, Germany • Kerpen, Germany • Leuna, Germany • Treviso, Italy • Congleton, UK • Greensboro, USA • Shenzhen, China • Zhuhai, China

For more information about ALBERDINGK BOLEY and our product offerings, visit www.alberdingk-boley.de.

Product Overview

	Primers / stabilisers	interior paints	silicate systems	facade paint	renders / plasters	fast drying system	color quartz renders	roof tiles	low VOC paints
AC 2003		x		x			x		x
AC 2006		x		x					x
AC 2008				x	x	x		x	
AC 2019				x	x		x		
AC 2022		x	x	x					x
AC 2025		x							x
AC 2077				x					
AC 548				x			x		
ALBO <i>rapid</i> 11						x			
AS 6004		x	x		x				x
AS 6900		x	x		x				x
CUR 751		x	x						x
H 595	x		(x)						
H 735	x								
Ren AC 8003		x		x			x		x
Ren AC 8025		x							x
Ren AS 7900		x	x		x				x
SC 4400			x	x	x				
SC 4450	(x)	(x)			x	x			
SC 48			x		x			x	

Last update
February 21, 2025

Page 5 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or a suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required

	PUD for exterior coatings	enamels / trim paints	stick to anything paints	wood stains	metal paints	stain locking primers	varnishes	floor paints
AC 2003					x	x	(x)	
AC 2019		x		x				
AC 2025		x						
AC 2360		x						
AC 2403			x		x	x		
AC 2420					x			
AC 25381		x					x	
AC 2700					x		x	x
AC 2714					x			x
AC 2736				x				
AC 3600		x					x	
AC 3626		x						
AC 3660			x					x
AC 3686		x						
AC 3687			x					x
AC 5401				x		x		
LUR 3				x				
Ren AC 8003					x	x	(x)	
Ren AC 8025		x						
Ren AC 8403			x		x	x		
Ren AC 8700					x		x	x
Ren AC 9630		x						
SC 48					x			
U 2101	x							
U 400 N	x							

Last update
February 21, 2025

Page 6 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC| USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or a suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required

Introduction

Decorative applications can be divided into the following sections of paints / primers and stabilizers

Interior paint binders

Low MFFT styrene acrylic and pure acrylic disperisons for high PVC paints.

ALBERDINGK® Ren AS 7900 is the latest invention with biobased monomer and similar performance to fossil styrene acrylics.

Styrene acrylics & pure acrylics

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2003	49.0-51.0	20-2,000	7.0-9.0	3	For class 1+2 paints, superior water resistance, ammonia neutralised
Ren AC 8003	49.0-51.0	20-2,000	7.0-9.0	3	Biobased, for class 1+2 paints, superior water resistance, ammonia neutralised (bio content: ca. 45%)
AC 2006	45.0-47.0	20-200	7.5-8.5	6	For interior and exterior flat to semi-gloss paints featuring superior scrub resistance
AC 2022	53.0-55.0	50-2,000	7.0-8.0	0	Pure acrylic for preservative-free paints with high pH value / silicate paints
AS 6004	49.5-51.0	200-2,000	8.0-9.0	0	For class 1+2 paints, silicate compatible, very hydrophobic
AS 6900	48.0-50.0	20-2,000	7.0-8.0	0	For class 1+2 paints, for class 1 silicate paints, low odour
Ren AS 7900	48.0-50.0	20-2,000	7.0-8.0	0	Biobased styrene acrylic for class 1+2 paints, for class 1 silicate paints, low odour (bio content: ca. 40%)

Last update
February 21, 2025

Page 7 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC| USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

Due to the new biocide restriction published in the 13th ATP of the CLP regulation and the new criteria for the german „Blauer Engel“ environmental logo (RAL-UZ 102) more and more preservative free or silicate paints are being produced.

ALBERDINGK BOLEY has a wide portfolio of silicate compatible dispersions with only CMIT preservation as well as for classical silicate paints which may still contain some traces of preservatives.

Special products such as **ALBERDINGK® AS 6500**, which is designed for long shelf life in silicate paints as well as scrub class 1 (EN 13 300) with only 5% organic content are most suitable for making future proof paints.

Styrene & pure acrylic for silicate and preservative free paints

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2022	53.0-55.0	50-2,000	7.0-8.0	0	Pure acrylic for preservative-free paints with high pH value / silicate paints


Multiphase acrylics for high stain resistant paints

For high resistant paints and for formulations with lower PVC levels, multiphase polymers which consist of hard and soft domains offer superior stain and wet scrub resistance combined with a block free surface.

ALBERDINGK® AC 2025 is particularly designed for low temperature film formation and excellent pigment wetting/binding capacity.

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2025	48.0-50.0	500-4,000	8.0-9.0	0	Multiphase acrylic, optimised for very high scrub and chemical resistance, excellent blocking resistance
Ren AC 8025	48.0-50.0	500-5,000	7.5-8.5	0	Biobased, multiphase acrylic, optimised for very high scrub and chemical resistance, excellent blocking resistance (bio content: ca. 38%)

Stain resistance-comparison:



White paint based on **ALBERDINGK® AC 2025** compared to a market standard

Renewable resource PUD & Acrylics

Paints which are based on renewable resources are becoming more and more attractive as consumers are looking for „green“ chemistry which is more environmental friendly.

ALBERDINGK® CUR 751 based paints reach approx. 80% of renewable content (incl. water). Since it's based on castor oil, it has a non-yellowing film and fast drying. Castor oil is ethically correct as it's not a food crop. Paints based on **ALBERDINGK® CUR 751** have no odor – unlike alkyd based paints.

Alberdingk®-product	Solids [%]	pH-value	MFFT [°C]	Features
CUR 751	34.0-36.0	7.0-8.5	0	Castor oil based PUD, class 2 paints with excellent wet scrub resistance and low odour (bio content: ca. 57%)
Ren AC 8003	49.0-51.0	7.0-9.0	3	Biobased pure acrylic for class 1+2 paints, superior water resistance, ammonia neutralized (bio content: ca. 45%)
Ren AC 8025	48.0-50.0	7.5-8.5	0	Biobased, multiphase acrylic, optimised for very high scrub and chemical resistance, excellent blocking resistance (bio content: ca. 38%)
Ren AS 7900	48.0-50.0	7.0-8.0	0	Biobased styrene acrylic for class 1+2 paints, for class 1 silicate paints, low odour (bio content: ca. 40%)

Primers / stabilisers

Hydrosols are used in stabilisers and primers since a long time. Ultra-fine particle size and excellent wetting and binding properties are key features of our hydrosols.

Hydrosol

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
H 595	29.0-31.0	20-35	7.5-9.0	0	Workhorse styrene acrylic hydrosol, silicate compatible
H 735	34.0-36.0	20-200	7.0-9.0	0	Pure acrylic hydrosol for solvent-free deep priming with very good intercoat adhesion on mineral substrates

Last update
February 21, 2025

Page 10 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

Exterior paints

Pure acrylics

Our pure acrylics are designed for long lasting exterior coatings. **ALBERDINGK® AC 2077** is developed for colour stable exterior coatings / house paints.

ALBERDINGK® Ren AC 8003 is a new biobased product with superior early water resistance and **ALBERDINGK® AC 2008** offers a very high solids which offers an extremely broad formulation latitude.

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2003	49.0-51.0	20-2,000	7.0-9.0	3	Superior water resistance, low surface tack
Ren AC 8003	49.0-51.0	20-2,000	7.0-9.0	3	Biobased, for class 1+2 paints, superior water resistance, ammonia neutralized (bio content: ca. 45%)
AC 2006	45.0-57.0	20-200	7.5-8.5	6	Superior scrub resistance, excellent non-leaching properties & water resistance
AC 2008	58.0-60.0	200-2,000	8.0-9.0	0	Ultra-high solids, suitable for fast drying systems, excellent weathering resistance, low surface tack
AC 2019	45.0-47.0	500-1,500	8.0-9.0	17	Universal, very good water resistance
AC 2022	53.0-55.0	50-2,000	7.0-8.0	0	Pure acrylic for preservative-free paints with high pH value / silicate paints
AC 2077	45.0-47.0	20-300	8.0-9.0	17	Wet adhesion promoted, with optimized colour stability
AC 548	49.0-51.0	3,000-6,000	7.5-8.5	13	Universal, very good water resistance

Styrene acrylics

Our styrene acrylics are workhorse products which find use in cost effective exterior coatings, thanks to the improved pigment binding capability of styrene.

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AS 6900	49.5-51.0	200-2,000	8.0-9.0	0	For class 1+2 paints, for class 1 silicate paints, low odour
Ren AS 7900	48.0-50.0	20-2,000	7.0-8.0	0	Biobased styrene acrylic for class 1+2 paints, for class 1 silicate paints, low odour
SC 48	49.0-51.0	3,000-5,000	7.0-7.5	14	Most hydrophobic styrene acrylic
SC 4400	49.0-51.0	2,000-5,000	7.0-8.0	17	Workhorse product, extremely versatile
SC 4450	49.5-51.0	500-5,000	7.5-8.5	18	Low odor, for indoor & outdoor, matt & glossy



Last update
February 21, 2025

Page 12 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or a suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required

Binders for renders / plasters

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2019	45.0-47.0	500-1,500	8.0-9.0	17	Universal, very good water resistance
AS 6900	49.5-51.0	200-2,000	8.0-9.0	0	For class 1+2 paints, for class 1 silicate paints, low odour
Ren AS 7900	48.0-50.0	20-2,000	7.0-8.0	0	Biobased styrene acrylic for class 1+2 paints, for class 1 silicate paints, low odour
SC 48	49.0-51.0	3,000-5,000	7.0-7.5	14	Most hydrophobic styrene acrylic
SC 4400	49.0-51.0	2,000-5,000	7.0-8.0	17	Workhorse product, extremely versatile
SC 4450	49.5-51.0	500-5,000	7.5-8.5	18	Low odor, for indoor & outdoor, matt & glossy



Last update
February 21, 2025

Page 13 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or a suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required

Binders for colour quartz renders

ALBERDINGK® acrylics for colour quartz renders offer superior early water resistance and long durability at various MFFT levels.

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 548	49.0-51.0	3,000-6,000	7.5-8.5	13	Universal, very good water resistance
AC 2003	49.0-51.0	20-2,000	7.0-9.0	3	Superior early water resistance, low surface tack
Ren AC 8003	49.0-51.0	20-2,000	7.0-9.0	3	Biobased pure acrylic for class 1+2 paints, superior water resistance, ammonia neutralised
AC 2019	45.0-47.0	500-1,500	8.0-9.0	17	Universal, very good water resistance, higher Tg



Last update
February 21, 2025

Page 14 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com


The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or a suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required

Fast drying acrylics for autumn / spring

ALBERDINGK's quick drying system based on controlled coagulation is based on **ALBERDINGK® AC 2008** (high solids pure acrylic) and **ALBERDINGK® ALBORapid 11** (coagulation polymer) for paints and renders which set quickly in marginal conditions.


Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2008	58.0-60.0	200-2,000	8.0-9.0	0	Ultra-high solids, suitable for fast drying systems, excellent weathering resistance, low surface tack
ALBORapid 11	24.0-26.0	100-1,000	10.4-11.4	n.a.	Additive polymer which can significantly increase the drying speed of water based coatings, recommended for alkaline substrates

Formulation with Dispersion and **ALBORapid** at high pH level



- Particles with electrostatic and steric stabilization
- High concentration of ammonia at high pH level
- Dissolved coagulation polymer without electrostatic charge at high pH level

Coagulation Mechanism of **ALBORapid**-base



PUDs for exterior coatings

Polyurethane dispersions in exterior masonry coatings are still „exotic“ due to their higher raw material cost. PUD's offer a non-tacky surface at very low T_g, combined with high elongation and superior colour stability compared to acrylic dispersions. Thanks to their high water vapor permeability and low water absorption they can be easily formulated into high performance paints.


Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
U 2101	59.5-61.5	600-1,400	7.5-9.5	0	Very high solids, excellent weathering resistance
U 400 N	39.0-41.0	20-200	7.0-8.0	0	Saponification and hydrolysis resistant, high water vapour permeability

Outdoor weathering resistance


Formulation FP 400-11 + 0.5% addition of 40% red pigment preparation:

Permanent Red FGR (Clariant, 17% s.o.p. DISPERBYK-199)

ALBERDINGK® U 400 N:



Competitor (optimized acrylic for coloured exterior paints)



Binders for multicolour paints (MCP)

Multicolour paints are using a special rheology / rheology modifier to have several colours in one paint. This requires polymer dispersions with very hydrophobic stabilization mechanism that reacts better with OPTIGEL®-thickeners.

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2019	45.0-47.0	500-1,500	8.0-9.0	17	Universal, very good water resistance
AC 2523	47.0-49.0	500-4,000	7.5-8.5	0	Multiphase, very good chemical resistance



Enamels / lacquers / trim paints / stains

ALBERDINGK offers a variety of acrylics for enamels – all based on multiphase technology to ensure excellent blocking and weathering resistance.

ALBERDINGK® AC 3600 and other members of the AC 36xx-family of products offer a significantly improved open time due to their special grafted hydrophilic stabilization system. AC 36xx products develop immediate blocking resistance and a very hard, almost solvent based like surface hardness even at low MFFT.

Acrylics for enamels

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2025	48.0-50.0	500-4,000	8.0-9.0	0	multiphase acrylic, optimized for very high gloss and chemical resistance
Ren AC 8025	48.0-50.0	500-5,000	7.5-8.5	0	Biobased, multiphase acrylic, optimised for very high scrub and chemical resistance, excellent blocking resistance
AC 2360	46.0-48.0	100-3,000	7.0-9.0	0	Multiphase, high gloss and good wet adhesion
AC 25381	47.0-49.0	2,000-8,000	7.5-8.5	9	Harder multiphase acrylic, very versatile and easy to formulate

Improved open time acrylics

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	features
AC 3600	40.0-42.0	20-200	7.5-8.5	0	Very hard with low MFFT, superior chemical and blocking resistance
AC 3626	39.0-41.0	50-200	8.0-9.0	45	Superior hand fat resistance
AC 3686	45.0-47.0	50-500	7.5-8.5	35	High quality gloss paints with excellent flow and levelling as well as long open time
Ren AC 9630	40.0-42.0	50-500	7.0-8.5	25	Biobased acrylic or high quality furniture coatings with excellent "Anfeuerung" and transparency



Last update
February 21, 2025

Page 20 of 36


Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com


The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or a suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required

AC 36xx-family stabilization system vs. conventional surfactant stabilization

Grafted electrosteric stabilization of particle in AC 36xx-family:




Conventional surfactant based electrosteric stabilization of particle:



Impact of stabilization on open time

AC 36xx-family:


- Strong repulsive force between the particles
- More hydrophilic particle surface



- ➔ Longer open time
- ➔ More newtonian, less thickener response

Conventional acrylics:

- Weaker repulsive force between the particles
- More hydrophobic particle surface



- ➔ Shorter open time
- ➔ Stronger thickener response

Last update
February 21, 2025

Page 22 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or a suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required

Open Time Test (ASTM D7488; 21°C 50% humidity)



t=15min

t=20min

t=25min

t=30min

t=35min

t=40min



Handfat resistance*


FP 3626-04

enamel for brush application

trade quality paint (alkyd/PUD)



FP 3626-04 = **ALBERDINGK® AC 3626**



*16h Alberdingk-fatty acid test which simulates the resistance of the film to human hand fat or hand lotions.

Visualisation of the softening by applying carbon black powder.

Last update
February 21, 2025

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Page 23 of 36

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

Acrylics for stick to anything paints

Multisubstrate or „stick to anything“ paints have become very popular over recent years. Combinations of **ALBERDINGK® AC 2403** (adhesion, hydrophobic properties) with harder polymers (**ALBERDINGK® AC 3687** or **ALBERDINGK® AC 3660**) to adjust application and mechanical properties are first choice for high class paints.

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2403	46.0-48.0	200-2,000	8.0-9.0	16	Best adhesion and super hydrophobic properties
Ren AC 8403	46.0-48.0	200-2,000	8.0-9.0	20	Biobased acrylic with highest corrosion resistance & universal adhesion
AC 3687	40.0-42.0	20-200	7.5-8.5	0	High hardness @low MFFT, enhanced open time
AC 3660	39.0-41.0	20-200	8.0-9.0	55	Highest chemical resistance, enhanced open time

Adhesion properties

FP 3600-05 stick to everything paint, white, multipurpose
(based on **ALBERDINGK® AC 3600** & **ALBERDINGK® AC 2403**)

Test	Substrates	Results*	Test Conditions
Adhesion (according to ISO 2409)	ABS	GT 1	Cross hatch cut, Tape peel-off
	PS	GT 2	
	PVC	GT 0	
	Steel	GT 1	
	Aluminium	GT 1	
	Galvanized steel	GT 1	
	Tiles	GT 0	

* GT 0 = best / Gt 5 = worst

Last update
February 21, 2025

Page 24 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com


Acrylics for trim paints

Full colour trim paints for wood can be based on economic single phase polymers such as **ALBERDINGK® AC 2019** and more sophisticated multiphase acrylics such as **ALBERDINGK® AC 25381**. In both cases a long durability is easily achieved.

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2019	45.0-47.0	500-1,500	8.0-9.0	17	Universal, very good water resistance
AC 25381	47.0-49.0	2,000-8,000	7.5-8.5	9	Workhorse polymer with excellent resistances and durability

Weathering resistance

Outdoor enamel formulation FP 2019-06 based on **ALBERDINGK® AC 2019**
after 4 years outdoor weathering



Last update
February 21, 2025

Page 25 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or a suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required

Binders for stains


Acrylic and Polyurethane dispersions for wood stains / decking. **ALBERDINGK® AC 2019** and **ALBERDINGK® AC 5401** are single phase, economic products.

ALBERDINGK® AC 2736 is a multiphase acrylic with very high water vapor permeability and Lignocure-technology, which allows a reaction with the lignin of the wood in order to avoid/retard the degradation of the lignin/wood.

ALBERDINGK® LUR 3 is a linseed oil based PUD with outstanding weathering resistance.

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	features
AC 2019	45.0-47.0	500-1,500	8.0-9.0	17	Universal, very good water resistance
AC 5401	48.0-50.0	200-1,500	8.0-9.0	5	Universal, excellent stain locking
AC 2736	39.0-41.0	50-2,000	8.0-9.0	0	High water vapor permeability, Lignocure-technology, blocking resistant
LUR 3	34.0-36.0	20-400	7.5-8.5	0	Linseed oil PUD, excellent weathering resistance

ALBERDINGK® AC 2736, wood stains in different colour shades after 5 years outdoor exposure:



Last update
February 21, 2025

Page 26 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or a suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required

Metal paints

Our acrylic dispersions for metal paints offer protection up to C5I-long level ! **ALBERDINGK® AC 2403** is the leading market standard in metal protection.


ALBERDINGK® AC 2003 and **ALBERDINGK® SC 48** are single phase, economic solutions for primers and paints.

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2003	49.0-51.0	20-2,000	7.0-8.0	3	Good corrosion resistance, economic
Ren AC 8003	49.0-51.0	20-2,000	7.0-9.0	3	Biobased acrylic with good weathering resistance, low water absorption
AC 2403	46.0-48.0	200-2,000	8.0-9.0	16	Highest corrosion resistance & universal adhesion
Ren AC 8403	46.0-48.0	200-2,000	8.0-9.0	20	Biobased acrylic with highest corrosion resistance & universal adhesion
AC 2420	46.0-48.0	200-3,000	8.0-9.0	20	Harder version of AC 2403, optimized for galvanized surfaces
SC 48	49.0-51.0	3,000-5,000	7.0-7.5	14	Good corrosion resistance, high PVC products, Zn-compatible

Test Results (after 1440 hours neutral salt-spray test)

FP 2403-78

anti-corrosion coatings, PVC approx. 11%,
solids approx. 49%, spray application, semi gloss recommended
nozzle size > 2.0 mm,
Gloss: approx. 85 @60°



Last update
February 21, 2025

Page 28 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

Stain locking primers

Stain locking primers with exceptional water resistance prevent stain migration without the use of heavy metals.

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2003	49.0-51.0	20-2,000	7.0-9.0	3	Good weathering resistance, low water absorption
Ren AC 8003	49.0-51.0	20-2,000	7.0-9.0	3	Biobased acrylic with good weathering resistance, low water absorption
AC 2403	46.0-48.0	200-2,000	8.0-9.0	16	Excellent stain locking, very good water barrier, improves intercoat adhesion
AC 5401	48.0-50.0	200-1,500	8.0-9.0	5	Economic and very versatile
Ren AC 8403	46.0-48.0	200-2,000	8.0-9.0	20	Biobased acrylic with excellent stain locking, very good water barrier, improves intercoat adhesion

Floor paints


1-pack, self-crosslinking multiphase acrylics with exceptional hot tire and chemical resistance.

ALBERDINGK® AC 3660 offers wet look when being formulated as clear coating.


Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2714	43.0-45.0	30-300	8.0-9.0	50	Very hydrophobic
AC 3660	39.0-41.0	20-200	8.0-9.0	55	Wet look, epoxy acrylic
AC 3687	40.0-42.0	20-200	7.5-8.5	0	Low VOC-applications

Hot tire resistance

ALBERDINGK® AC 3660:



commercial product:




Varnishes

Varnishes for DIY offer low co-solvent demand combined with high chemical resistance.

ALBERDINGK® AC 2700 offers a good compromise of hand fat and general chemical resistance – **ALBERDINGK® AC 3600** has best application properties (flow, levelling & open time) combined with „snap drying“.

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AC 2700	42.0-44.0	50-500	7.0-8.0	0	Good hand fat resistance, very good sanding properties
Ren AC 8700	42.0-44.0	500-4,000	7.0-8.0	4	Biobased acrylic with good hand fat resistance, very good sanding properties
AC 25381	47.0-49.0	2,000-8,000	7.5-8.5	9	Universal product with very good chemical resistance, economic
AC 3600	40.0-42.0	20-200	7.5-8.5	0	Outstanding hardness and sanding properties, clear in the can



Last update
February 21, 2025

Page 31 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

Construction products

Waterproofing

ALBERDINGK® AS 2040 is a workhorse styrene acrylic for sealants, waterproofing, etc. Our polyurethane dispersions offer excellent hydrolysis resistance, low Tg and very low dirt pickup.

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AS 2040	59.0-58.0	1,500-4,500	7.0-9.0	0	Tg -8°C, universal compatibility (especially with cement)
U 2101	59.5-61.5	600-1,400	7.5-9.5	0	Very high solids, excellent weathering resistance
U 228	59.0-61.0	200-1,000	7.5-9.5	0	Superior hydrolysis resistance
U 400 N	39.0-41.0	20-200	7.0-8.0	0	Highest hydrolysis and alkaline resistance



Last update
February 21, 2025

Page 32 of 36


Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or a suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required

Film Properties

Tensile strength and elongation of the free film (according to DIN EN ISO 527-1)



Last update
February 21, 2025

Page 33 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or a suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required

Grouts and mortars

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AS 2040	59.0-58.0	1,500-4,500	7.0-9.0	0	Tg -8°C, universal compatibility (especially with cement)
SC 4400	49.0-51.0	2,000-5,000	7.0-8.0	17	Universal, odorless, tough-elastic, water- and alkali resistant



Ceramic tiles

Alberdingk®-product	Solids [%]	Viscosity [mPas]	pH-value	MFFT [°C]	Features
AS 2110	49.0-51.0	1,000-2,000	6.8-7.2	3	For waterproofing, cement-free tile adhesives and primers on difficult substrates
AS 2120	49.0-51.0	500-2,000	7.0-8.0	17	For waterproofing, cement-free tile adhesives and primers on difficult substrates

Last update
February 21, 2025

Page 34 of 36

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Zhuhai) Co., Ltd. | Zhuhai City | P. R. China | www.alberdingkresins.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or a suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required

Disclaimer:

While the descriptions, data and information (collectively, the "Information") contained herein, or otherwise made available to or used by a customer, potential customer and/or user (each, a "User"), represent our current state of technology and are presented in good faith and believed to be accurate, they are provided for guidance purposes only. Alberdingk Boley itself and on behalf of all of its past, current and future affiliated and related companies and entities (hereinafter referred to as "AB") make no warranties (expressed or implied), as to the Information's accuracy, sufficiency, adequacy or freedom from defect and assumes no liability in connection with any use of the Information. The Information is not intended to assure certain characteristics of AB's products and their suitability for particular application fields and/or uses, as many factors may affect processing, application and/or use. Any User of AB's products is responsible for determining the suitability of such products for its particular application. No express or implied warranty is made by AB of the merchantability, suitability, fitness for a particular purpose, freedom from patent infringement or otherwise of any product or service. Any existing intellectual/industrial property rights must be observed. AB will not be liable to any User for any damages including, without limitation, any special, incidental or consequential damages. In no case shall any Information provided to a User be considered part of AB's terms and conditions of sale.

**ALBERDINGK BOLEY**

Alberdingk Boley GmbH
Düsseldorfer Str. 53 | 47829 Krefeld | Germany
Tel +49 2151 528-0 | Fax +49 2151 573643
info@alberdingk-boley.de | www.alberdingk-boley.de

